



AVIN SHIMI JAHAN

Avin Chemistry
General Trading Company
Iranian Bitumen Exporter

MC70 Cutback Bitumen

MC70 Specifications

Priming of all non-bituminous road bases , provision of temporary surfaces (deviations)

Typical Physical & Performance Properties

Application Rate	From 0,6 litre per m2 to 1,2 litre/m2	
Spraying/Application Temperature	60° - 80° C	
Ductility @ 25 deg. C.	100 min	
Appearance	Black	
	Min	Max
Kinematic Viscosity 60°C, cSt	70	140
Distillation @ 101,325 kPa	-	-
Distillate, % by Vol. of Total Distillate to 360°C	Min	Max
to 190° C	-	-
to 225° C	10	50
to 260° C	40	80
to 316° C	80	95
Residue from Distillation to 360°C, % Vol. of Original Sample	55	-
	Min	Max
Penetration at 25°C on Residue from Distillation	90	180



Unit 11, 4th Floor, No.22, 6th Alley, Ahmad Ghasir St,
Shahid Beheshti Av. Tehran - Iran



+98 - 21 - 88 17 08 22 - 7



+98 - 21 -88 17 08 28



+98 -912 - 220 13 95



info@avinchemistry.com